


AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:



Claims 1-58 (Canceled)

59. (Currently Amended) A process for the preparation of a low-viscosity (poly)isocyanate composition comprising at least one isocyanate dimer containing a uretidinedione unit and at least 1 weight % of at least one carbamate function, from starting isocyanate monomers in which the isocyanate groups are borne by sp^3 carbon atoms, comprising the step of heating a starting reaction medium comprising said isocyanate monomers, in the absence of a dimerization catalyst, to a temperature of at least 50°C and of not more than 200°C for a period of not more than 24 hours, the reaction medium containing the starting monomers also containing a compound of general formula I:




in which R is a mono- or n-valent hydrocarbon group having from 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears 1 to 3 OH groups, and n is an integer ranging from 1 to 3, said composition optionally containing products derived from reaction of said compound of formula I with a compound bearing an aliphatic isocyanate function.

60. (Currently Amended) A process according to claim 59, comprising adding to the reaction medium containing the starting monomers a compound of general formula II and/or III below:




in which one or more of X_1 , X_2 and X_3 represents a group $R'-(N=C=O)_p$ in which R' is an aliphatic group and p is an integer ranging from 0 to 5, the others representing, a group of formula




R_1 is a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears

1 to 3 OH groups, with the OH groups optionally substituted, with a group CONX₁H, X₁ being as defined above, at least one of NX'₁X''₁, NX'₂X''₂ and NX'₃X''₃ represents the group,



the others representing a group NX₁H or NX₁-silyl and R₂ being a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally, bears 1 to 3 OH groups, with the OH groups optionally substituted, with a group CONX₁H, or




and n is an integer ranging from 1 to 3.

61. (Previously Presented) A process according to Claim 59, wherein R is a C₁-C₄ alkyl group substituted with 1 to 3 OH groups.


62. (Previously Presented) A process according to Claim 60, wherein said compound of general formula I is selected from pentaerythritol or trimethylolpropane, and the compounds of general formulae II and III are selected from the corresponding pentaerythritol or trimethylolpropane derivatives of general formula II or III or both II and III wherein R₁ or R₂ or both R₁ and R₂ represents a group selected from CH₂OH or CH₃CH₂.

Claims 63-65 (Canceled)


66. (Currently Amended) A composition comprising at least one compound of general formula X:



in which R' is an aliphatic group and p is an integer ranging from 0 to 5, and at least one compound of general formula II:




in which one or more of X₁, X₂ and X₃ represents a group -R'(-N=C=O)_p and the others represent, a group




and R_1 is a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH group, with the OH groups optionally substituted with a group CONX_1H wherein X_1 represents $\text{R}'\text{---}(\text{N}=\text{C}=\text{O})_p$

and n is an integer from 1 to 3;

and/or at least one compound of general formula III:




in which at least one of $\text{NX}'_1\text{X}''_1$, $\text{NX}'_2\text{X}''_2$ and $\text{NX}'_3\text{X}''_3$ represents the group,




the others representing a group NX_1H and

R_2 being a hydrocarbon group having 1 to 30 carbon atoms, in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and

optionally, bears 1 to 3 OH groups, with the OH groups optionally substituted with a group CONX₁H or




and optionally a biuret compound containing an isocyanate group of general formula VI




said composition further comprising at least 1 weight % of at least one carbamate group and being free of dimerization catalyst selected from phosphine; aminopyridine, phosphoramidate, organometallic or tertiary amine.

67. (Previously Presented) A composition according to Claim 66, further comprising a compound of general formula VIII:



and/or a compound of general formula XIII:




wherein R'' represents H or a hydrocarbon group.


68. (Canceled)

$$\text{R}_2 - \text{C} \begin{bmatrix} \text{CH}_2\text{OCONX}'_1\text{X}''_1 \\ \text{CH}_2\text{OCONX}'_2\text{X}''_2 \\ \text{CH}_2\text{OCONX}'_3\text{X}''_3 \end{bmatrix}_n \quad (\text{III})$$

at least one of $NX'_1X''_1$, $NX'_2X''_2$ and $NX'_3X''_3$ represents the group




in which R' is an aliphatic group and p is an integer ranging from 0 to 5, the others representing a group NX₁H with X₁ representing a group R'-(N=C=O)_p and R₂ being a hydrocarbon group having 1 to 30 carbon atoms in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH groups, with the OH groups optionally substituted with a group CONX₁H, or



and


n is an integer ranging from 1 to 3.

70. (Currently Amended) A compound comprising at least 1.0 weight % carbamate groups, the compound formed according to of the formula III




in which:


the groups $\text{NX}'_1\text{X}''_1$, $\text{NX}'_2\text{X}''_2$ and $\text{NX}'_3\text{X}''_3$ are selected from a group of general formula NX_1H , with X_1 representing a group $\text{R}'-(\text{N}=\text{C}=\text{O})_p$ in which R' is an aliphatic group and p is an integer from 0 to 5, or a group of general formula V,




or a uretidinedione group of formula IV,



or an isocyanurate group of formula XI:



or, a biuret group of formula XII:



wherein R'' represents H or a hydrocarbon group, R₂ being a hydrocarbon group having 1 to 30 carbon atoms in which the hydrocarbon chain optionally is interrupted by one or more chalcogen atoms and optionally bears 1 to 3 OH groups and n is an integer ranging from 1 to 3, wherein the optional OH groups in R₂ are optionally

$$\begin{array}{c} \text{---CO---N---R'---(N=C=O)}_p \\ | \\ \text{C---NH---R'---(N=C=O)}_p \\ || \\ \text{O} \end{array} \quad (\text{VI})$$

- at least one composition according to Claim 66; and
- an acrylate polyol which satisfies the following conditions for a dry extract:
 - Mw (weight-average molecular weight) not greater than 10,000;- Mn (number-average molecular weight) of not greater than 5000;
 - Mw/Mn (dispersity ratio) of not greater than 5;
 - number of OHs/molecule of greater than or equal to 2.

75. (Previously Presented) A composition comprising:

- at least one composition according to Claim 66; and
- a polyester polyol having a viscosity of not greater than 10,000 mPa.s at 25°C, and an Mw of between 250 and 8000.

76. (Previously Presented) A composition according to Claim 73, containing a crosslinking catalyst, which is optionally a latent catalyst.

77. (New) The process of claim 59, wherein the (poly)isocyanate composition comprises at least 1 weight % carbamate.